

COMS ★ P85 85-305185/49 ★ FR 2563-229-A
 Organic electrochromic material grafted on pyrrole polymer - used
 in display devices


COMMISS ENERGIE ATOMIQUE 20.04.84-FR-006902
 A85 L03 U11 (25.10.85) C08g-73/06 C09k-09/02 C25b-03/02 G09f-
 09/80

20.04.84 as 006902 (950RP)

An organic electrochrome material comprises an organic
 electrochrome molecule (I) grafted on a polymer of pyrrole or of its
 deriv. Pref. (I) comprises 4,4'-bipyridinium (viologene) or
 phthalocyanine partic. lucethium diphtalocyanine or a cpd. of
 formula (II).

A film of the material is deposited on an electrode by passing an
 electric current between that electrode and a counter electrode, both
 dipped in a bath comprising pyrrole or its derivs. chemically linked
 to an organic electrochrome molecule, an electrolyte support and a
 solvent.

USE/ADVANTAGE - In display devices. Good adhesion is
 achieved between a film of the material and an electrode. (7pp
 Dwg.No.0/0) N85-226889



© 1985 DERWENT PUBLICATIONS LTD.

128, Theobalds Road, London WC1X 8RP, England

US Office: Derwent Inc. Suite 500, 6845 Elm St. McLean, VA 22101

Unauthorised copying of this abstract not permitted.